

A method of making wet rolls includes providing a web of material, applying a wetting solution to the web to produce a wet web, and winding the wet web into a roll. The wetting solution may be applied at an add-on greater than 25%, and the web may travel at a speed of at least 60 meters per minute.

5